

Madras® Crossing Glossy

Technical data sheet

Rev. 06.04.2018

Manufacturer: Vitrealpecchi spa

Base product: float glass to EN 572 1-2; laminated float glass to UNI EN ISO 12543.

Description and performance:

translucent glass with permanent chemical etching on one side and characterized by high light transmission and a particularly silky touch. The décor is mat and perfectly smooth. This special finish thus ensures easier cleaning than traditional satin-finish glass, in both the processing and maintenance phases.

Sheet sizes: 2250/2400 x 3210 mm (usable sizes: 2210/2360 x 3170 mm).

Thicknesses: monolithic float glass 4/5/6/8/10/12 mm; laminated float glass 33.1.

Colours: extraclear, clear, dark grey.
*Availability of standard colours/
thicknesses is subject to change.
Please verify when ordering.*

Weight: 2.5 kg/m² per millimetre of thickness.

Compatible processing: all mechanical and thermal processes associated with glass: cutting, grinding, bevelling, drilling, laminating, toughening, bending, double glazing, painting, enamelling etc.

Cleaning: care must be taken when installing the glass not to get putty, resin, sealants, etc., on the treated side. Each of these substances requires a specific solvent for removing traces from glass. For routine maintenance, use water and/or any of the commonly marketed glass detergents. Dry immediately with a clean cloth - preferably micro-fibre - by wiping repeatedly gently in the same direction.

Storage and handling:

- it is advisable to unpack immediately after reception and store in a dry, well-ventilated place free from sudden changes of temperature to avoid condensation;
- never store outdoors;



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

Madras® Crossing Glossy

- when storing for over 3 months, it's advisable to remove the paper from between the plates;
- in case of storage in unfavourable environmental conditions (high humidity and strong temperature changes), it is advisable to slightly space one plate from another;
- storing for more than 12 months is not advisable;
- to avoid scratching the surface of the glass during handling and storage, plates should always be separated by means of spacers.

Internal and external applications:

building, doors and windows, furnishing, work tops, display surfaces, IWBs, etc.

Processing defects acceptance limits:

defects visible from a distance of min. 1.5 m.

Float defects acceptance limits: as per UNI EN 572.2.

Vitrealpecchi Spa

Via IV Novembre 95
22066 Mariano Comense CO
Italy
T. +39 031 745062
E. info@vitrealpecchi.it



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.